Laird TECHNOLOGIES

Innovative **Technology** for a **Connected** World

Tputty™ 504 Series



SOFT, SILICONE GEL

Tputty™ 504 is a soft silicone gel thermal gap filler ideal for applications where large gap tolerances are present.

The silicone gel is filled with a complex matrix of ceramic fillers to yield superior thermal performance.

Tputty™ 504 is soft and compliant transferring little to no pressure between interfaces. Because Tputty™ 504 has a higher viscosity than grease, it eliminates the bleed and pump-out usually associated with grease. Bond line variances can also be more easily controlled than with traditional thermal pads.

Tputty™ 504 can be applied like grease and is easily dispensable from a wide range of commercially available equipment including screen print, syringe and automated equipment.

FEATURES AND BENEFITS

- Soft and compliant transferring little to no pressure between interfaces
- 1.8 W/mK thermal conductivity
- Available in 10cc, 30cc and 55cc syringes
- Available in 100cc,170cc and 305cc auto dispense cartridges
- Available in bulk containers from sample jars through 20 kg pails
- Applies like grease and is easily dispensable from a wide range of commercially available equipment including screen print, syringe and automated equipment

APPLICATIONS

- Flip chip microprocessors
- PPGAs, micro BGAs, BGAs
- DSP chips, graphic accelerator chips
- Other high-wattage electronic components
- LED lighting

global solutions: local support™

Americas: +1.800.843.4556
Europe: +49.8031.2460.0
Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com
www.lairdtech.com/thermal

Laird TECHNOLOGIES

Innovative **Technology** for a **Connected** World

Tputty™ 504 Series

	Tputty™ 504	TEST METHOD
Construction & Composition	Ceramic-filled dispensable silicone gel	
Color	Light Grey	Visual
Viscocity @ 23°C, mPa.s (cP) Brookfield RV, TC spindle, Helipath @ 0.5 rpm	4,000,000 to 8,000,000	
Temperature Range	-45°C to 200°C	
Thermal Conductivity	1.8 W/mK	ASTM D5470
Density	2.7 g/cc	
Thermal Impendance Final Thickness @ 0.010"	0.15°C-in²/W (0.97°C-cm²/W)	ASTM D5470 (modified)
Thermal Impendance Final Thickness @ 0.020"	0.27°C-in²/W (1.74°C-cm²/W)	ASTM D5470 (modified)
Dielectric Strength	500 VAC/mil	ASTM D149
Volume Resistivity	$>10^{14}$ ohm-cm	ASTM D2240
MSDS	Available upon request	
Outgassing TML, wt% / vol%	0.34 / 0.92	ASTM E595
Outgassing CVCM, wt% / vol%	0.09 / 0.24	ASTM E595

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2011 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.
A13850-00 Rev I, 11/2011

OCEAN CHIPS
Океан Электроники
Поставка электронных компонентов

Компания «Океан Электроники» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Поставка оригинальных импортных электронных компонентов напрямую с производств Америки, Европы и Азии, а так же с крупнейших складов мира;
- Широкая линейка поставок активных и пассивных импортных электронных компонентов (более 30 млн. наименований);
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Помощь Конструкторского Отдела и консультации квалифицированных инженеров;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Поставка электронных компонентов под контролем ВП;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- При необходимости вся продукция военного и аэрокосмического назначения проходит испытания и сертификацию в лаборатории (по согласованию с заказчиком);
- Поставка специализированных компонентов военного и аэрокосмического уровня качества (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Actel, Aeroflex, Peregrine, VPT, Syfer, Eurofarad, Texas Instruments, MS Kennedy, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Компания «Океан Электроники» является официальным дистрибьютором и эксклюзивным представителем в России одного из крупнейших производителей разъемов военного и аэрокосмического назначения «**JONHON**», а так же официальным дистрибьютором и эксклюзивным представителем в России производителя высокотехнологичных и надежных решений для передачи СВЧ сигналов «**FORSTAR**».

AVIC JONHON

«JONHON» (основан в 1970 г.)

Разъемы специального, военного и аэрокосмического назначения:

(Применяются в военной, авиационной, аэрокосмической, морской, железнодорожной, горно- и нефтедобывающей отраслях промышленности)

«FORSTAR» (основан в 1998 г.)

ВЧ соединители, коаксиальные кабели, кабельные сборки и микроволновые компоненты:

(Применяются в телекоммуникациях гражданского и специального назначения, в средствах связи, РЛС, а так же военной, авиационной и аэрокосмической отраслях промышленности).

FORSTAR®

Телефон: 8 (812) 309-75-97 (многоканальный)
Факс: 8 (812) 320-03-32
Электронная почта: ocean@oceanchips.ru
Web: http://oceanchips.ru/
Адрес: 198099, г. Санкт-Петербург, ул. Калинина, д. 2, корп. 4, лит. А