

Self-Laminating Translucent Vinyl Film

This specification is intended to outline the physical properties of *PANDUIT*'s pressure sensitive self-laminating translucent vinyl material and include the following part numbers and printable material identifiers:

| Part Number Prefixes | |
|----------------------|------------|
| PSCB-*-Y | PSWMH-*-Y |
| PSCC-*-Y | PDL* |
| PSM-*-Y | PLD-VBGSLY |
| PSWM-*-Y | |

| Printable Material Suffixes | | |
|-----------------------------|--|--|
| VADY | | |
| VAFY | | |
| VARY | | |
| | | |

PRODUCT SPECIFICATIONS:

| | |
|----------------------------------|---|
| Description: | Material is RoHS compliant (European Union directive 2002/95/EC). Material is a self-extinguishing top coated vinyl film with a pressure sensitive adhesive. This material is used in a self-laminating format for wire/cable marking. |
| Print Methods: | This material is preprinted and recommended for dot matrix and thermal transfer printing. |
| Adhesive: | Acrylic based, pressure sensitive high tack adhesive. |
| Standard Colors: | Translucent film with colored print-on area |
| Thickness: | 4.25 +/- 0.45 mils (substrate and adhesive) |
| Service Temperature Range: | -40°F to 150°F (-40°C to 66°C) |
| Minimum Application Temperature: | 40°F (4.4°C) |
| Storage Conditions: | Store at 70°F (21°C) and 50% Relative Humidity. |

PROPERTIES:

PERFORMANCE:

| | |
|-----------------------------------|---|
| Peel Adhesion to Stainless Steel: | 32 oz/in width (PSTC-101, 15 min. dwell) 45 oz/in width (PSTC-101, 24 hrs dwell) |
| Shear Adhesion: | 24+ hours (PSTC-107, Procedure A) |
| Tensile Strength: | MD 12.2 +/- 1.5 lbs./inch width minimum (PSTC-131) 3200 PSI minimum (ASTM D882) |
| Elongation: | MD 150% minimum (PSTC-131) 150% minimum (ASTM D882) |
| UV Resistance: | *3000 hours no change observed (ASTM G154) |
| Elevated Temperature Exposure: | After 8 hours at 150°F (65.5°C) there was no deterioration of the substrate |
| Flammability: | Average burn time less than 10 seconds (ASTM D1000) |
| Dielectric Strength: | 1,900 Volts/Mil (ASTM D-149-97, Method A) |

*3000 hours equates to 5 years of assimilated outdoor UV exposure.

CHEMICAL/SOLVENT RESISTANCE:

Samples were preprinted, dot matrix printed with Panduit dot matrix ribbon, and thermal transfer printed with RMH*BL/RMEH*BL ribbon. These samples were wrapped around a 1/12" OD wire in self-laminating format. Test was conducted at room temperature after 24 hour dwell. The samples were immersed in the specified chemical reagents for 5 immersions using the following cycle: a 10 minute immersion time followed by a 30 minute recovery time.

| Chemical Reagent | Visual Observation | | | |
|-------------------------------|-----------------------|----------------------------|---------------------------|---------------------------------|
| | Substrate / Adhesive | Pre-Printed Printed Legend | Dot Matrix Printed Legend | Thermal Transfer Printed Legend |
| Distilled Water | No effect | No effect | No effect | No effect |
| Mineral Spirits | Slight adhesive bleed | No effect | No effect | No effect |
| ASTM #3 Oil | Slight adhesive bleed | No effect | No effect | No effect |
| Isopropyl Alcohol | No effect | No effect | No effect | No effect |
| Methanol | No effect | No effect | No effect | No effect |
| 3% Alconox Detergent | Slight adhesive bleed | No effect | No effect | No effect |
| 10% Sodium Hydroxide Solution | No effect | No effect | No effect | No effect |
| 10% Sulfuric Acid Solution | No effect | No effect | No effect | No effect |
| 5% Sodium Chloride Solution | No effect | No effect | No effect | No effect |
| Freon TF | No effect | No effect | No effect | No effect |
| Super Agitene | Slight adhesive bleed | No effect | No effect | No effect |
| Jet-A Fuel | Slight adhesive bleed | No effect | No effect | No effect |
| Arco TruSlide 68 | No effect | No effect | No effect | No effect |
| SAE 30 Motor Oil | No effect | No effect | No effect | No effect |

APPROVALS

UL recognized: UL 969 File Number: MH14576 (PSM-*-Y, PLD-VBGS LY), MH14979 (PDL*, VADY)

CUL recognized: C22.2 No 0.15-01 File Number: MH14576 (PSM-*-Y, PLD-VBGS LY), MH14979 (PDL*, VADY)

PSCB-*-Y, PSCC-*-Y, PSWM-*-Y, PSWMH-*-Y, VAFY, and VARY are not UL or CUL recognized

LIMITED WARRANTY

All *PANDUIT* Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of *PANDUIT* printers with any product other than the specified *PANDUIT* products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER *PANDUIT* OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

Компания «Океан Электроники» предлагает заключение долгосрочных отношений при поставках импортных электронных компонентов на взаимовыгодных условиях!

Наши преимущества:

- Поставка оригинальных импортных электронных компонентов напрямую с производств Америки, Европы и Азии, а так же с крупнейших складов мира;
- Широкая линейка поставок активных и пассивных импортных электронных компонентов (более 30 млн. наименований);
- Поставка сложных, дефицитных, либо снятых с производства позиций;
- Оперативные сроки поставки под заказ (от 5 рабочих дней);
- Экспресс доставка в любую точку России;
- Помощь Конструкторского Отдела и консультации квалифицированных инженеров;
- Техническая поддержка проекта, помощь в подборе аналогов, поставка прототипов;
- Поставка электронных компонентов под контролем ВП;
- Система менеджмента качества сертифицирована по Международному стандарту ISO 9001;
- При необходимости вся продукция военного и аэрокосмического назначения проходит испытания и сертификацию в лаборатории (по согласованию с заказчиком);
- Поставка специализированных компонентов военного и аэрокосмического уровня качества (Xilinx, Altera, Analog Devices, Intersil, Interpoint, Microsemi, Actel, Aeroflex, Peregrine, VPT, Syfer, Eurofarad, Texas Instruments, MS Kennedy, Miteq, Cobham, E2V, MA-COM, Hittite, Mini-Circuits, General Dynamics и др.);

Компания «Океан Электроники» является официальным дистрибьютором и эксклюзивным представителем в России одного из крупнейших производителей разъемов военного и аэрокосмического назначения «JONHON», а так же официальным дистрибьютором и эксклюзивным представителем в России производителя высокотехнологичных и надежных решений для передачи СВЧ сигналов «FORSTAR».



JONHON

«JONHON» (основан в 1970 г.)

Разъемы специального, военного и аэрокосмического назначения:

(Применяются в военной, авиационной, аэрокосмической, морской, железнодорожной, горно- и нефтедобывающей отраслях промышленности)

«FORSTAR» (основан в 1998 г.)

ВЧ соединители, коаксиальные кабели, кабельные сборки и микроволновые компоненты:

(Применяются в телекоммуникациях гражданского и специального назначения, в средствах связи, РЛС, а так же военной, авиационной и аэрокосмической отраслях промышленности).



Телефон: 8 (812) 309-75-97 (многоканальный)

Факс: 8 (812) 320-03-32

Электронная почта: ocean@oceanchips.ru

Web: <http://oceanchips.ru/>

Адрес: 198099, г. Санкт-Петербург, ул. Калинина, д. 2, корп. 4, лит. А